

Designation: awmoho01a-01 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, SP


## External wall - awmoho01 a-01

external wall, solid wood construction, not ventilated, without dry lining, with cladding, other surface

### Performance rating

**REI** from inside 60 Fire protection performance REI from outside 30 maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 35,0 kN/m Classified by HFA

Thermal performance	U Diffusion	0.22 W/(m <sup>2</sup> K) suitable
Calculated by HFA		
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>I</sub> )	51(-3;-9) dB
Assessed by TU-GRAZ		
Mass per unit area	m	72.40 kg/m <sup>2</sup>



Note: When using cross laminated timber: Variation 02-03: d  $\geq$  94,0; at least 3-layers, top layer at least 30mm; variation 00-01: d  $\geq$  78,0; at least 3-layers, top layer at least 25mm

## Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
			λ	μ min – max	ρ	С	EN
4	20.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	30.0	spruce wood battens (30/60)	0.120	50	450	1.600	D
С		vapour-permeable membrane $sd \le 0.3 m$					
D	80.0	spruce wood battens (40/50 or 80/60;e=625)	0.120	50	450	1.600	D
E	80.0	mineral wool [040; ≥70; ≥1000°C]	0.040	1	70	1.030	A1
F	80.0	mineral wool [040; ≥70; ≥1000°C]	0.040	1	70	1.030	A1
G	80.0	solid glued wood (e.g. cross laminated timber)	0.130	50	500	1.600	D
Н	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

# Sustainability rating (per m<sup>2</sup>)

Database ecoinvent	
OI3 <sub>Kon</sub>	50.4
Calculated by HFA	



Designation: awmoho01a-01 8/2/23 Holzforschung Austria Last updated:

Source:

Editor: HFA, SP

## Details of sustainability rating

### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.258	0.087	2,97E-6	0.098	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	90.684	797.085	887.769	650.418	19.804	670.221