

Designation: awmopi01a-02 8/2/23 Last updated:

Holzforschung Austria Source:

Editor: HFA, PLB

# External wall - awmopi01a-02

external wall, solid wood construction, not ventilated, with dry lining, with rendering, other surface

## Performance rating

**REI** from inside 90 Fire protection performance RFI from outside 90

maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 35,0 kN/m Classified by HFA

#### Germany

REI60 (from inside/from outside); Attention: REI 90 (from inside) in Germany possible with 2x12,5mm gypsum plaster board type DF/gypsum fibre board Load E<sub>d,fi</sub> according to the German certification document


Corresponding proof: manufacturer-specific

Thermal performance	U Diffusion	0.18 W/(m <sup>2</sup> K) suitable
Calculated by HFA Calculated by TUM		
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>l</sub> )	50(-3;-9) dB

Rw=48dB if a lightweight ETICS insulation panel ( $\varrho$  approx. 90kg/m³) is applied. Assessed by Müller-BBM

Mass per unit area 97.40 kg/m<sup>2</sup>

Calculation based on gypsum plaster board type DF



Note: Attention: REI90 (from inside) in Germany possible with 2x12,5mm gypsum plaster board type DF/gypsum fibre board

# Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
			λ	μ min – max	ρ	С	EN
Α	7.0	plaster	1.000	10 - 35	2000	1.130	A1
В	140.0	mineral wool MW-PT [041; 155] ETICS insulation panel	0.041	1	155	1.030	A1
С	100.0	cross laminated timber	0.130	50	500	1.600	D
D	70.0	spruce wood battens (60/60) mounted on resilient clips; e=660	0.120	50	450	1.600	D
E	50.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
F	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
F	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

## Sustainability rating (per m<sup>2</sup>)

Database ecoinvent		Database GaBi (ÖKOBAUDAT)				
OI3 <sub>Kon</sub>	82.3	Built-in renewable materials	kg	51.830		
Calculated by HFA		Biogenic carbon in kg CO <sub>2</sub> -e.	kg CO <sub>2</sub>	74.710		
Calculated by TITA		Energy use of Primary Energy	MJ	864.810		
		Share of renewable PE	%	28.41		

Calculated by TUM



Designation: awmopi01a-02 Last updated:

8/2/23 Holzforschung Austria Source:

HFA, PLB Editor:

## Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.394	0.127	4,24E-6	0.147	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	56.248	731.169	787.416	936.905	17.714	954.619

#### Database GaBi (ÖKOBAUDAT)

Lifecycle	GWP	AP	EP	ODP	POCP
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]
A1 - A3		0.229	0.036	3,30E-6	0.022
C1 - C4		0.005	0.007	1,53E-7	0.001
A1 - C4		0.237	0.043	3,46E-6	0.022

Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	244.511	888.138	1130.439	594.367	37.891	631.720
C1 - C4	0.803	-879.492	-878.525	18.411	0.000	20.620
A1 - C4	245.701	8.905	252.764	619.109	37.943	662.090