

Designation: awmopi03a-01 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, PLB

External wall - awmopi03a-01

external wall, solid wood construction, not ventilated, with dry lining, with rendering, other surface

Performance rating

REI from inside Fire protection 90 RFI from outside 90 performance

maximum ceiling height = 3 m; maximum load $E_{d,fi}$ = 35,0 kN/lfm

Classified by HFA

Germany

REI 60 (from inside)/REI90 (from outside); Attention: REI90 (from inside) possible with 2x12,5mm gypsum plaster board type DF/gypsum fibre board

Load E_{d,fi} according to the German certification document

Corresponding proof: manufacturer-specific

Thermal performance U $0.09 \text{ W/(m}^2\text{K)}$ Diffusion suitable

The stated thermal characteristics in the product data sheet are specified for the hard board intermediate web; the flanges are calculated with solid wood. Calculated by HFA


Calculated by TUM

Acoustic performance R_w (C;C_{tr}) 63(-2;-7) dB $L_{n,w}$ (C_l)

Assessed by Müller-BBM

Mass per unit area 106.40 kg/m^2

Calculation based on gypsum plaster board type DF



Note: Attention: REI 90 (from inside) in Germany possible with 2x12,5mm gypsum plaster board type DF/gypsum fibre board

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal pe	Reaction to fire			
			λ	μ min – max	ρ	С	EN
Α	7.0	plaster	1.000	10 - 35	2000	1.130	A1
В	60.0	wood-fibre insulation board [045; 190]		5 - 7	190	2.100	E
С	300.0	Light composite wood-based beams (I-beams) with solid wood flanges ($60/45$) and hard board intermediate web ($\geq 6,7$) e= 625	0.400	20 - 30	800	1.700	D
D	300.0	Wood fibre insulation [039; 45]	0.039	1 - 2	45	2.100	E
E	100.0	cross laminated timber ≥ 94,0; at least 3-layers, top layer at least 30 mm	0.130	50	500	1.600	D
F	70.0	spruce wood Battens on resilient clips (60/60; e=625)	0.120	50	450	1.600	D
G	50.0	Wood fibre insulation [039; 45]	0.039	1 - 2	45	2.100	E
Н	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
Н	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

Sustainability rating (per m²)

Database ecoinvent

48.0

calculated with gypsum plaster fire protection board (GKF/DF); this data includes 3-, 5-, and 7-ply cross laminated timber elements;

Calculated by HFA

Database GaBi (ÖKOBAUDAT)

Built-in renewable materials	kg	88.120
Biogenic carbon in kg CO ₂ -e.	kg CO₂	126.670
Energy use of Primary Energy	MJ	1842.400
Share of renewable PE	%	42.80

Calculated by TUM



Designation: awmopi03a-01 Last updated:

8/2/23 Holzforschung Austria Source:

Editor: HFA, PLB

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.231	0.102	4,53E-6	0.053	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]

Database GaBi (ÖKOBAUDAT)

Lifecycle	GWP	AP	EP	ODP	POCP
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]
A1 - A3		0.206	0.044	3,27E-6	0.042
C1 - C4		0.004	0.001	1,48E-7	0.000
A1 - C4		0.212	0.046	3,42E-6	0.043

Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	785.206	1890.085	2672.416	1007.876	82.002	1089.390
C1 - C4	2.908	-1884.283	-1881.210	40.501	-70.799	-28.090
A1 - C4	788.495	6.061	792.051	1053.901	11.255	1070.240