

Designation: awmopi04a-00 8/2/23 Last updated:

Holzforschung Austria Source:

Editor: HFA, PLB

# External wall - awmopi04a-00

external wall, solid wood construction, not ventilated, with dry lining, with rendering, other surface

#### Performance rating

**REI** from inside Fire protection 90 RFI from outside 60 performance

maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 35 kN/lfm Classified by HFA

Thermal performance U  $0.09 \text{ W/(m}^2\text{K)}$ Diffusion suitable


The stated thermal characteristics in the product data sheet are specified for the hard board intermediate web; the flanges are calculated with solid wood. Calculated by HFA


 $R_w$  (C;C<sub>tr</sub>) 49 dB Acoustic performance  $L_{n,w}$  ( $C_l$ )

without resilient clips  $Rw \ge 46 dB$ Assessed by HFA

Mass per unit area  $110.80 \text{ kg/m}^2$ 

Calculation based on gypsum plaster board type DF





### Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
			λ	μ min – max	ρ	С	EN
Α	4.0	plaster	1.000	10 - 35	2000	1.130	A1
В	60.0	mineral wool MW-PT [040; 155]	0.040	1	155	1.030	A1
С	15.0	fibreboard (MDF)	0.140	11	600	1.700	D
D	300.0	Light composite wood-based beams (I-beams) with solid wood flanges ( $60/45$ ) and hard board intermediate web ( $\geq 6,7$ ) e= $625$	0.400	20 - 30	800	1.700	D
E	300.0	Cellulose fibre [040; 50]	0.040	1	50	2.000	E
F	100.0	cross laminated timber $d \ge 94,0$ ; at least 3-layers, top layer at least 30mm;	0.130	50	500	1.600	D
G	80.0	spruce wood	0.120	50	450	1.600	D
Н	80.0	Cellulose fibre [040; 50]	0.040	1	50	2.000	Е
T	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
Ι	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

#### Sustainability rating (per m<sup>2</sup>)

Database ecoinvent

calculated with gypsum plaster fire protection board (GKF/DF) and silicate plaster; this data includes 3-, 5-, and 7-ply cross laminated timber elements; Calculated by HFA



Designation: awmopi04a-00 8/2/23 Holzforschung Austria Last updated:

Source:

HFA, PLB Editor:

## Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.320	0.118	4,12E-6	0.092	
Lifecycle	PERE	PERM	DEDT	DENIDE	DENIDAA	DENIBT
Lifetytic	PENE	PERIVI	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]