

Designation: awrhhi01a-06 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, SP

## External wall - awrhhi01 a-06

external wall, timber frame construction, ventilated, with dry lining, with cladding, other surface

#### Performance rating


**REI** from inside 45 Fire protection performance REI from outside 30 maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 19,2 kN/m Classified by HFA

Thermal performance  Calculated by HFA	U Diffusion	0.14 W/(m <sup>2</sup> K) suitable
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> )	52(-3;-10) dB

Battens for the ventilation space screwed onto the structural timber together with vertical battens for the dry lining screwed directly onto the ledger beams will result in Rw(C;Ctr)=43(-1;-5) dB Assessed by MA39

Mass per unit area  $51.50 \text{ kg/m}^2$ 

Calculation based on GF



Note: e=625

# Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal pe	Thermal performance			
			λ	μ min – max	ρ	С	EN
Α	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	30.0	spruce wood battens offset (30/50; 30/80) - ventilation	0.120	50	450	1.600	D
С		wind barrier			1000		
D	12.5	gypsum fibre board	0.320	21	1000	1.100	A2
E	240.0	construction timber (60/; e=*)	0.120	50	450	1.600	D
F	240.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
G	10.0	gypsum fibre board	0.320	21	1000	1.100	A2
Н		vapour barrier sd≥ 2m			1000		
1	80.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
J	80.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
K	12.5	gypsum fibre board or	0.320	21	1000	1.100	A2
K	12.5	gypsum plaster board type DF	0.250	10	800	1.050	A2

## Sustainability rating (per m²)

Database ecoinvent						
OI3 <sub>Kon</sub>	30.1					
Calculated by HFA						



Designation: awrhhi01a-06 Last updated:

8/2/23 Holzforschung Austria Source:

HFA, SP Editor:

#### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.136	0.063	2.73E-6	0.026	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	108.575	523.820	632.395	469.134	10.862	479.997