

Designation: awrhhi01b-00 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, SP

## External wall - awrhhi01 b-00

external wall, timber frame construction, ventilated, with dry lining, with cladding, other surface

#### Performance rating


**REI** from inside 60 Fire protection performance REI from outside 60 maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 19,2 kN/m Classified by HFA

Thermal performance  Calculated by HFA	U Diffusion	0.22 W/(m <sup>2</sup> K) suitable
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n.w</sub> (C <sub>l</sub> )	51(-2;-8) dB

Battens for the ventilation space screwed onto the structural timber together with vertical battens for the dry lining screwed directly onto the ledger beams will result in Rw(C;Ctr)=44(-1;-5) dB Assessed by MA39

Mass per unit area  $55.90 \text{ kg/m}^2$ 

Calculation based on GF



Note: e=625

# Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
			λ	μ min – max	ρ	С	EN
Α	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	30.0	spruce wood battens offset (30/50; 30/80) - ventilation	0.120	50	450	1.600	D
С		wind barrier			1000		
D	20.0	gypsum fibre board (2x10 mm)	0.320	21	1000	1.100	A2
Е	160.0	construction timber (60/; e=*)	0.120	50	450	1.600	D
F	160.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
G	12.5	gypsum fibre board	0.320	21	1000	1.100	A2
Н		vapour barrier sd≥ 2m			1000		
1	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
J	40.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
K	12.5	gypsum fibre board or	0.320	21	1000	1.100	A2
K	12.5	gypsum plaster board type DF	0.250	10	800	1.050	A2

## Sustainability rating (per m<sup>2</sup>)

Calculated by HFA

Database ecoinvent OI3<sub>Kon</sub> 25.1



Designation: awrhhi01b-00 Last updated:

8/2/23 Holzforschung Austria Source:

HFA, SP Editor:

## Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.106	0.050	2,43E-6	0.020	
	,				'	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	88.181	411.795	499.975	404.466	10.862	415.328