

Designation: awrhhi04a-12 Last updated: 8/2/23

Holzforschung Austria Source:

В

Editor: HFA, SP

## External wall - awrhhi04a-12

external wall, timber frame construction, ventilated, with dry lining, with cladding, other surface

#### Performance rating

**REI** from inside 60 Fire protection performance REI from outside 30

maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 19,2 kN/m

Classified by HFA Classified by HFA

F60 (from inside)/F30 (from outside)

Load  $\boldsymbol{E}_{d,fi}$  according to the German certification document

Corresponding proof: manufacturer-specific

Thermal performance	U Diffusion	0.21 W/(m <sup>2</sup> K)
Calculated by TUM	2	Salvasie
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>I</sub> )	50(-3;-10) dB
Assessed by Müller BBM		
Mass per unit area	m	61.10 kg/m <sup>2</sup>

С Е F G Н I D

Note: dry lining ≥ 40 mm

Calculation based on gypsum plaster board type DF

# Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
				μ min – max	ρ	С	EN
Α	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	30.0	spruce wood battens offset (30/50; 30/80) - ventilation	0.120	50	450	1.600	D
С	15.0	fibreboard (MDF)	0.140	11	600	1.700	D
D	160.0	construction timber (60/; e=625)	0.120	50	450	1.600	D
E	160.0	Wood fibre insulation [039; 45]	0.039	1 - 2	45	2.100	E
F	15.0	OSB	0.130	200	600	1.700	D
G	40.0	spruce wood cross battens (a=400) $\geq$ 40mm	0.120	50	450	1.600	D
Н	40.0	Wood fibre insulation [039; 45]	0.039	1 - 2	45	2.100	Е
I	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
1	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

## Sustainability rating (per m<sup>2</sup>)

Database ecoinvent		Database GaBi (ÖKOBAUDAT)			
OI3 <sub>Kon</sub> Calculated by HFA	17.8	Built-in renewable materials Biogenic carbon in kg CO <sub>2</sub> -e.	kg kg CO <sub>2</sub>	55.550 80.470	
Calculated by HTA		Energy use of Primary Energy	MJ	1073.290	
		Share of renewable PE	%	37.91	

Calculated by TUM



Designation: awrhhi04a-12 Last updated: 8/2/23

Source: Holzforschung Austria

Editor: HFA, SP

#### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.104	0.045	1,78E-6	0.023	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
Lifecycle (Phases)	PERE [MJ]	PERM [MJ]	PERT [MJ]	PENRE [MJ]	PENRM [MJ]	PENRT [MJ]

#### Database GaBi (ÖKOBAUDAT)

Lifecycle	GWP	AP	EP	ODP	POCP
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]
A1 - A3		0.121	0.026	1,56E-6	0.035
C1 - C4		0.002	0.000	1,01E-7	0.000
A1 - C4		0.125	0.027	1,67E-6	0.035

Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	404.519	1253.161	1657.532	636.693	56.945	693.710
C1 - C4	1.957	-1248.914	-1246.958	24.516	-56.003	-31.490
A1 - C4	406.855	4.505	411.213	666.439	0.994	667.510