

Designation: awrhhi06a-10 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, SP

External wall - awrhhi06a-10

external wall, timber frame construction, ventilated, with dry lining, with cladding, other surface

Performance rating

REI from inside Fire protection 60 performance REI from outside 30 maximum ceiling height = 3 m; maximum load $E_{d,fi}$ = 19,2 kN/m Classified by HFA

Thermal performance	U Diffusion	0.22 W/(m ² K) suitable
Calculated by HFA		
Acoustic performance	R _w (C;C _{tr}) L _{n,w} (C _l)	51(-3;-10) dB


Battens for the ventilation space screwed onto the structural timber together with vertical battens for the dry lining screwed directly onto the ledger beams will result in Rw(C;Ctr)=44(-2;-5)

Assessed by MA39

Calculated by HFA

Mass per unit area $49.40~\textrm{kg/m}^2$

Calculation based on gypsum plaster board type DF



Note: e=625

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire	
			λ	μ min – max	ρ	С	EN	
Α	24.0	larch wood external wall cladding	0.155	150	600	1.600	D	
В	30.0	spruce wood battens offset (30/50; 30/80) - ventilation	0.120	50	450	1.600	D	
С		wind barrier			1000			
D	25.0	planking spruce wood	0.120	50	450	1.600	D	
E	160.0	construction timber (60/; e=*)	0.120	50	450	1.600	D	
F	160.0	sheep wool [0,041; R=26]	0.041	1	30	1.720	Е	
G	25.0	planking spruce wood	0.120	50	450	1.600	D	
Н		vapour barrier sd≥ 5m			1000			
I	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D	
J	40.0	sheep wool [0,041; R=26]	0.041	1	30	1.720	E	
K	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2	
K	12.5	gypsum fibre board	0.320	21	1000	1.100	A2	

Sustainability rating (per m²) Database ecoinvent OI3_{Kon}



Designation: awrhhi06a-10 8/2/23 Holzforschung Austria Last updated:

Source:

HFA, SP Editor:

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.086	0.038	1,84E-6	0.007	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	50.805	932.229	983.034	304.656	14.585	319.241