

Designation: awrhhi08b-07 8/2/23 Last updated:

Holzforschung Austria Source:

Editor: HFA, SP

### External wall - awrhhi08b-07

external wall, timber frame construction, ventilated, with dry lining, with cladding, other surface


#### Performance rating

**REI** from inside 60 Fire protection performance REI from outside 60 maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 19,2 kN/m Classified by HFA

Thermal performance  Calculated by HFA	U Diffusion	0.19 W/(m <sup>2</sup> K) suitable
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>l</sub> )	53(-2;-8) dB

Battens for the ventilation space screwed onto the structural timber together with vertical battens for the dry lining screwed directly onto the ledger beams will result in Rw(C;Ctr)=46(-1;-5) dB Assessed by MA39

Calculation based on GF



Note: e=625

## Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	Thermal performance			
		λ	μ min – max	ρ	С	EN	
Α	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	30.0	spruce wood battens offset (30/50; 30/80) - ventilation	0.120	50	450	1.600	D
С		wind barrier			1000		
D	20.0	gypsum fibre board (2x10 mm)	0.320	21	1000	1.100	A2
E	160.0	mineral wool [035; 50; <1000°C]	0.035	1	50	1.030	A1
F	160.0	construction timber (60; e=*)	0.120	50	450	1.600	D
G	15.0	OSB (sealed with airtight tape)	0.130	200	600	1.700	D
Н	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
I	40.0	mineral wool [035; 50; <1000°C] or air layer in type 02	0.035	1	50	1.030	A1
J	15.0	gypsum fibre board or	0.320	21	1000	1.100	A2
J	15.0	gypsum plaster board type DF	0.250	10	800	1.050	A2

# Sustainability rating (per m<sup>2</sup>)

Database ecoinvent						
OI3 <sub>Kon</sub>	49.7					
Calculated by HEA						



Designation: awrhhi08b-07 8/2/23 Holzforschung Austria Last updated:

Source:

HFA, SP Editor:

### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.213	0.095	4,10E-6	0.011	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	115.409	567.917	683.326	710.338	19.334	729.673