dataholz.eu

Designation: Last updated: Source: Editor: awrhhi12a-03 8/2/23 Holzforschung Austria HFA, PLB

External wall - awrhhi12a-03

external wall, timber frame construction, ventilated, with dry lining, with cladding, other surface

Performance rating

| Fire protection performance | REI from inside REI from outside | 30 30 | | | | | | |
|---|---|---------------------------------------|--|--|--|--|--|--|
| maximum ceiling height = Classified by HFA | = 3 m; maximum load E _{d,} | fi = 32 kN∕m | | | | | | |
| Germany | | | | | | | | |
| F30 (from inside/from ou | tside) | | | | | | | |
| Load E _{d.fi} according to the German certification document | | | | | | | | |
| Corresponding proof: DIN | 4102-4:2016-05, Tabel | le 10.7, Zeile 1 | | | | | | |
| Thermal performance | U Diffusion | 0.17 W/(m ² K) suitable | | | | | | |
| Calculated by TUM | | | | | | | | |
| Acoustic performance | R _w (C;C _{tr}) L _{n,w} (C _l) | 53(-1;-6) dB | | | | | | |
| Assessed by Müller-BBM | | | | | | | | |
| Mass per unit area | m | 67.50 kg/m ² | | | | | | |



Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

| | Thickness | Building material | Thermal pe | Reaction to fire | | | |
|---|-----------|--|------------|------------------|------|-------|----|
| | | | λ | µ min – max | ρ | с | EN |
| А | 24.0 | larch wood external wall cladding | 0.155 | 150 | 600 | 1.600 | D |
| В | 30.0 | larch wood battens offset (30/50; 30/80) - ventilation | 0.155 | 150 | 600 | 1.600 | D |
| С | | wind barrier | | | 1000 | | |
| D | 15.0 | fibreboard (MDF) | 0.140 | 11 | 600 | 1.700 | D |
| Е | 200.0 | construction timber (60/; e=625) | 0.120 | 50 | 450 | 1.600 | D |
| F | 200.0 | mineral wool [040; 30; ≥1000 °C] | 0.040 | 1 | 30 | 1.030 | A1 |
| G | 15.0 | OSB | 0.130 | 200 | 600 | 1.700 | D |
| Н | 40.0 | spruce wood cross battens (a=400) \ge 40mm | 0.120 | 50 | 450 | 1.600 | D |
| I | 40.0 | mineral wool [040; 30; ≥1000 °C] | 0.040 | 1 | 30 | 1.030 | A1 |
| J | 12.0 | OSB | 0.130 | 200 | 600 | 1.700 | D |
| К | 12.5 | gypsum plaster board type A | 0.250 | 4 - 10 | 680 | 1.050 | A2 |

Sustainability rating (per m²)

| Database ecoinvent | Database GaBi (ÖKOBAUDAT) | | | |
|---|---------------------------|--|-------------------------------------|--------------------------------------|
| OI3 _{Kon} Calculated by TUM | 35.2 | Built-in renewable materials Biogenic carbon in kg CO ₂ -e. Energy use of Primary Energy Share of renewable PE | kg kg CO ₂ MJ % | 53.880 78.940 784.010 29.35 |

dataholz.eu

Designation: Last updated: Source: Editor: awrhhi12a-03 8/2/23 Holzforschung Austria HFA, PLB

Details of sustainability rating

Database ecoinvent

| Lifecycle | GWP | AP | EP | ODP | POCP | |
|-----------|--------------------------|--------------------------|--------------------------|-------------|---------------|---------|
| (Phases) | [kg CO ₂ -e.] | [kg SO ₂ -e.] | [kg PO ₄ -e.] | [kg R11-e.] | [kg Ethen-e.] | |
| A1 - A3 | | 0.179 | 0.071 | 2,71E-6 | 0.009 | |
| | | | | | | |
| Lifecycle | PERE | PERM | PERT | PENRE | PENRM | PENRT |
| (Phases) | [M] | [M] | [M] | [LM] | [MJ] | [MJ] |
| A1 - A3 | 127.654 | 834.285 | 961.938 | 548.785 | 48.370 | 597.154 |

Database GaBi (ÖKOBAUDAT)

| Lifecycle | GWP | AP | EP | ODP | POCP | |
|-----------|--------------------------|--------------------------|--------------------------|-------------|---------------|---------|
| (Phases) | [kg CO ₂ -e.] | [kg SO ₂ -e.] | [kg PO ₄ -e.] | [kg R11-e.] | [kg Ethen-e.] | |
| A1 - A3 | | 0.144 | 0.024 | 1,85E-6 | 0.034 | |
| C1 - C4 | | 0.003 | 0.003 | 1,06E-7 | 0.000 | |
| A1 - C4 | | 0.148 | 0.027 | 1,96E-6 | 0.034 | |
| | | | | | | |
| Lifecycle | PERE | PERM | PERT | PENRE | PENRM | PENRT |
| (Phases) | [LM] | [M] | [LM] | [LM] | [MJ] | [M] |
| A1 - A3 | 228.599 | 917.264 | 1145.870 | 534.085 | 38.788 | 572.970 |
| C1 - C4 | 1.150 | -911.635 | -910.487 | 13.219 | -26.477 | -13.260 |
| A1 - C4 | 230.137 | 5.888 | 236.030 | 553.871 | 12.364 | 566.330 |