dataholz.eu

Designation: Last updated: Source: Editor: awrhho05a-00 8/2/23 Holzforschung Austria HFA, SP

External wall - awrhho05a-00

external wall, timber frame construction, ventilated, without dry lining, with cladding, other surface

Performance rating

e protection formance	REI from inside REI from outside	30 30
aximum ceiling height = assified by MA39 assified by HFA	= 3 m; maximum load E _{d,f}	; = 32,0 kN∕m
Thermal performance	U Diffusion	0.27 W∕(m ² K) suitable
Calculated by HFA	Diriusion	Juliubie
Acoustic performance	R _w (C;C _{tr}) L _{n,w} (C _l)	45(-2;-8) dB
Battens for the ventilation Rw(C;Ctr)=41(-1;-7) dB Assessed by MA39	n space screwed onto the	structural timber result in an
Mass per unit area	m	29.10 kg/m ²
Calculation based on GF		

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	rformance			Reaction to fire
			λ	µ min – max	ρ	с	EN
٩	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
3	30.0	spruce wood battens offset (30/50; 30/80) - ventilation	0.120	50	450	1.600	D
2	15.0	fibreboard (MDF)	0.140	11	600	1.700	D
)	160.0	construction timber ($60/; e=625$)	0.120	50	450	1.600	D
	160.0	mineral wool [040; ≥16; <1000 °C]	0.040	1	16	1.030	A1
:		vapour barrier sd≥ 1 m			1000		
5	15.0	gypsum fibre board or	0.320	21	1000	1.100	A2
5	15.0	gypsum plaster board type DF	0.250	10	800	1.050	A2

Sustainability rating (per m²)

Database ecoinvent

OI3_{Kon} Calculated by HFA 19.1

dataholz.eu

Designation: Last updated: Source: Editor: awrhho05a-00 8/2/23 Holzforschung Austria HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.095	0.042	1,62E-6	0.018	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
				ra 4 13		68.4.13
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]

dataholz.eu – Catalogue of timber building materials, components and component connections reviewed to consider thermal, acoustic, fire performance requirements and ecological drivers for timber construction released by accredited testing institutes. These datasheets will generally be accepted as proofs of compliance by building authorities.