dataholz.eu

Designation: Last updated: Source: Editor: awrhho05a-11 8/2/23 Holzforschung Austria HFA, SP

External wall - awrhho05a-11

external wall, timber frame construction, ventilated, without dry lining, with cladding, other surface

Performance rating

e protection formance ximum ceiling height = 3 ssified by HFA ssified by HFA (from inside/from outsi d E _{d,fi} according to the G responding proof: manuf ermal performance	REI from inside REI from outside m; maximum load E _d , de) erman certification doo acturer-specific U Diffusion	30 30 $32,0 \text{ kN/m}$ cument $0.21 \text{ W/(m}^2\text{K)}$ suitable
tic performance ed by Müller-BBM	R _w (C;C _{tr}) L _{n,w} (C _l)	46(-2;-8) dB
Mass per unit area Calculation based on gypsur	m n plaster board type D	53.30 kg/m ²

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal pe	Reaction to fire			
			λ	µ min – max	ρ	с	EN
А	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	30.0	spruce wood battens offset (30/50; 30/80) - ventilation	0.120	50	450	1.600	D
С	15.0	fibreboard (MDF)	0.140	11	600	1.700	D
D	200.0	construction timber (60/; e=625)	0.120	50	450	1.600	D
Е	200.0	Wood fibre insulation [039; 45]	0.039	1 - 2	45	2.100	E
F		vapour barrier sd≥ 1 m			1000		
G	15.0	gypsum fibre board or	0.320	21	1000	1.100	A2
G	15.0	gypsum plaster board type DF	0.250	10	800	1.050	A2

Sustainability rating (per m²)

OI3 _{Kon} Calculated by HFA	16.4	Built-in renewable materials Biogenic carbon in kg CO ₂ -e. Energy use of Primary Energy Share of renewable PE	kg kg CO ₂ MJ %	43.260 61.780 882.630 39.39
		Calculated by TUM		

Database GaBi (ÖKOBAUDAT)

dataholz.eu

Designation: Last updated: Source: Editor: awrhho05a-11 8/2/23 Holzforschung Austria HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.089	0.040	1,58E-6	0.019	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[LM]	[M]	[M]	[LM]	[MJ]	[LM]
A1 - A3	114.482	689.502	803.985	330.013	36.514	366.527

Database GaBi (ÖKOBAUDAT)

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.101	0.022	1,48E-6	0.024	
C1 - C4		0.002	0.000	1,00E-7	0.000	
A1 - C4		0.105	0.023	1,59E-6	0.024	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[M]	[LM]	[LM]	[MJ]	[M]
A1 - A3	345.724	1017.437	1363.436	505.816	55.964	561.870
C1 - C4	1.466	-1013.150	-1011.684	22.556	-47.077	-24.520
A1 - C4	347.668	4.546	352.490	534.964	8.951	544.010