dataholz.eu

Designation: Last updated: Source: Editor: awrhho05a-12 8/2/23 Holzforschung Austria HFA, SP

External wall - awrhho05a-12

external wall, timber frame construction, ventilated, without dry lining, with cladding, other surface

Performance rating

Fire protection performance naximum ceiling height = Classified by HFA Lassified by HFA	REI from inside REI from outside = 3 m; maximum load E _{d,1}	30 30 ₁ = 32,0 kN∕m
Germany F30 (from inside/from ou Load E _{d,fi} according to the	utside) e German certification doo	cument
Thermal performance	U Diffusion	0.18 W/(m ² K) suitable
Acoustic performance Assessed by Müller-BBM	R _w (C;C _{tr}) L _{n,w} (C _l)	47(-2;-8) dB
Mass per unit area Calculation based on gyp	m sum plaster board type D	53.40 kg/m²

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material Thermal performance					Reaction to fire
			λ	µ min – max	ρ	с	EN
А	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	30.0	spruce wood battens offset (30/50; 30/80) - ventilation	0.120	50	450	1.600	D
С	15.0	fibreboard (MDF)	0.140	11	600	1.700	D
D	240.0	construction timber (60/; e=625)	0.120	50	450	1.600	D
Е	240.0	mineral wool [040; 30; ≥1000°C]	0.040	1	30	1.030	A1
F		vapour barrier sd≥ 1 m			1000		
G	15.0	gypsum fibre board or	0.320	21	1000	1.100	A2
G	15.0	gypsum plaster board type DF	0.250	10	800	1.050	A2

Sustainability rating (per m²)

Database ecoinvent

OI3_{Kon} Calculated by HFA	25.8	Built-in renewable materials Biogenic carbon in kg CO ₂ -e. Energy use of Primary Energy Share of renewable PE Calculated by TLIM	kg kg CO ₂ MJ %	35.210 50.310 505.320 31.61

Database GaBi (ÖKOBAUDAT)

dataholz.eu

Designation: Last updated: Source: Editor: awrhho05a-12 8/2/23 Holzforschung Austria HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.138	0.047	1,46E-6	0.049	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[LM]	[M]	[LM]	[LM]	[MJ]	[LM]
A1 - A3	108.499	572.689	681.188	355.965	22.510	378.474

Database GaBi (ÖKOBAUDAT)

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.107	0.018	1,71E-6	0.015	
C1 - C4		0.002	0.003	1,05E-7	0.000	
A1 - C4		0.112	0.021	1,83E-6	0.016	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[M]	[MJ]	[LM]	[MJ]	[M]
A1 - A3	158.803	594.499	753.732	326.311	34.648	361.070
C1 - C4	0.441	-588.918	-588.476	11.428	-15.119	-3.690
A1 - C4	159.731	5.840	166.001	345.584	19.593	365.290