

Designation: awrhho05a-06 Last updated: 8/2/23

Source: Holzforschung Austria

Editor: HFA, SP

External wall - awrhho05a-06


external wall, timber frame construction, ventilated, without dry lining, with cladding, other surface

Performance rating

Classified by MA39 Classified by HFA

Thermal performance	U Diffusion	0.27 W/(m ² K) suitable
Calculated by HFA		
Acoustic performance	R _w (C;C _{tr}) L _{n,w} (C _l)	45(-2;-8) dB
Battens for the ventilation Rw(C;Ctr)=41(-1;-7) dB Assessed by MA39	1 space screwed onto	the structural timber result in an

Calculation based on GF



Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal pe	rformance			Reaction to fire
			λ	μ min – max	ρ	С	EN
Α	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	30.0	spruce wood battens offset (30/50; 30/80) - ventilation	0.120	50	450	1.600	D
С	15.0	fibreboard (MDF)	0.140	11	600	1.700	D
D	160.0	construction timber (60/; e=625)	0.120	50	450	1.600	D
E	160.0	Cellulose fibre [040; 50]	0.040	1	50	2.000	E
F		vapour barrier sd≥ 1 m			1000		
G	15.0	gypsum fibre board or	0.320	21	1000	1.100	A2
G	15.0	gypsum plaster board type DF	0.250	10	800	1.050	A2

Sustainability rating (per m²)

Database ecoinvent

Ol3_{Kon} 13.5

Calculated by HFA



Designation: awrhho05a-06 8/2/23 Holzforschung Austria Last updated:

Source:

HFA, SP Editor:

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.082	0.035	1,28E-6	0.016	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
		590.894	691.386	257.651	22.510	280.161