

Designation: awrohi02a-01 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, SP

# External wall - awrohi02a-01

external wall, timber frame construction, not ventilated, with dry lining, with cladding, other surface

## Performance rating


Fire protection **REI** from inside 60 performance REI from outside 30 maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 19,2 kN/m Classified by HFA

Thermal performance	U Diffusion	0.20 W/(m <sup>2</sup> K) suitable
Calculated by HFA		
Acoustic performance	$R_w$ (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>l</sub> )	49(-3;-9) dB
Vertical battens for the dr Rw(C:Ctr)=46(-1:-5) dB	y lining screwed onto	the ledger beams lead to an

Assessed by MA39

Mass per unit area  $62.00 \text{ kg/m}^2$ 

Calculation based on GF



Note: e=625

### Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal pe	Thermal performance			
		λ	μ min – max	ρ	С	EN	
Α	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	50.0	spruce wood cross battens	0.120	50	450	1.600	D
С	40.0	softboard [045; 250] - rigid underlay	0.045	5	250	2.100	E
D	15.0	fibreboard (MDF)	0.140	11	600	1.700	D
E	120.0	construction timber (60/; e=*)	0.120	50	450	1.600	D
F	120.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
G	15.0	OSB (sealed with airtight tape)	0.130	200	600	1.700	D
Н	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
ı	40.0	mineral wool [040; ≥16; <1000°C] or air layer in type 02	0.040	1	16	1.030	A1
	12.5	gypsum fibre board or	0.320	21	1000	1.100	A2
J	12.5	gypsum plaster board type DF	0.250	10	800	1.050	A2

## Sustainability rating (per m<sup>2</sup>)

Database ecoinvent

27.8 OI3<sub>Kon</sub>

Calculated by HFA



Designation: awrohi02a-01 8/2/23 Holzforschung Austria Last updated:

Source:

HFA, SP Editor:

### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.142	0.063	2,44E-6	0.027	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	134.991	841.912	976.903	486.524	42.896	529.420