

Designation: awrohi03a-09 8/2/23 Last updated:

Holzforschung Austria Source:

Editor: HFA, SP

External wall - awrohi03a-09

external wall, timber frame construction, not ventilated, with dry lining, with cladding, other surface

Performance rating

REI from inside 60 Fire protection performance RFI from outside 30 maximum ceiling height = 3 m; maximum load $E_{d,fi}$ = 32,0 kN/m Classified by HFA


Thermal performance Calculated by HFA	U Diffusion	0.18 W/(m ² K) suitable
Acoustic performance	R _w (C;C _{tr}) L _{n.w} (C _l)	50(-3;-9) dB

Vertical external battens and vertical battens for the dry lining screwed onto the ledger beams lead to an Rw(C;Ctr)=43(-1;-5) dB Assessed by MA39

Mass per unit area	m	76.70 kg/m²

Calculation based on GF

Calculated by HFA



Note: e=625

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance Reaction to fire				
			λ	μ min – max	ρ	С	EN
Α	24.0	larch wood external wall cladding	0.155	150	600	1.600	D
В	65.0	spruce wood cross battens of battens offset	0.120	50	450	1.600	D
С	50.0	wood wool composite boards	0.090	2 - 5	370	2.000	В
D	16.0	particleboard	0.130	50 - 100	700	1.700	D
Е	160.0	construction timber (60/; e=*)	0.120	50	450	1.600	D
F	160.0	cellulose fibre [0,040; R=55]	0.040	1 - 2	55	2.000	В
G	12.0	particleboard	0.130	50 - 100	700	1.700	D
Н		vapour barrier sd≥ 10m			1000		
1	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
J	40.0	cellulose fibre [040; E]	0.040	1 - 2	55	2.000	E
K	12.5	gypsum fibre board or	0.320	21	1000	1.100	A2
K	12.5	gypsum plaster board type DF	0.250	10	800	1.050	A2

Sustainability rating (per m²) Database ecoinvent 20.9 OI3_{Kon}



Designation: awrohi03a-09 Last updated:

8/2/23 Holzforschung Austria Source:

Editor: HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.114	0.047	1,96E-6	0.028	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	105.628	878.892	984.520	419.734	41.362	461.096