

Designation: awroho01a-02 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, SP

External wall - awroho01a-02


external wall, timber frame construction, not ventilated, without dry lining, with cladding, other surface

Performance rating

Fire protection **REI** from inside 30 performance **REI** from outside maximum ceiling height = 3 m; maximum load $E_{d,fi}$ = 32,0 kN/m Classified by HFA

| Thermal performance | U Diffusion | 0.18 W/(m ² K) suitable |
|----------------------|---|------------------------------------|
| Calculated by HFA | | |
| Acoustic performance | R _w (C;C _{tr}) L _{n,w} (C _l) | 51(-2;-7) dB |
| Assessed by MA39 | | |
| Mass per unit area | m | 73.30 kg/m ² |

Calculation based on GF



Note: e=625

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

| | Thickness | Building material | Thermal pe | rformance | | | Reaction to fire |
|---|-----------|-----------------------------------|------------|-------------|------|-------|------------------|
| | | | λ | μ min – max | ρ | С | EN |
| Α | 24.0 | larch wood external wall cladding | 0.155 | 150 | 600 | 1.600 | D |
| В | 24.0 | spruce wood cross battens | 0.120 | 50 | 450 | 1.600 | D |
| С | 50.0 | wood wool composite boards | 0.090 | 2 - 5 | 370 | 2.000 | В |
| D | 15.0 | fibreboard (MDF) | 0.140 | 11 | 600 | 1.700 | D |
| E | 200.0 | construction timber (60/; e=*) | 0.120 | 50 | 450 | 1.600 | D |
| F | 200.0 | mineral wool [040; ≥16; <1000°C] | 0.040 | 1 | 16 | 1.030 | A1 |
| G | 15.0 | OSB (sealed with airtight tape) | 0.130 | 200 | 600 | 1.700 | D |
| Н | 12.5 | gypsum fibre board or | 0.320 | 21 | 1000 | 1.100 | A2 |
| Н | 12.5 | gypsum plaster board type DF | 0.250 | 10 | 800 | 1.050 | A2 |

Sustainability rating (per m²)

Database ecoinvent

 013_{Kon} 27.8

Calculated by HFA



Designation: awroho01a-02 8/2/23 Holzforschung Austria Last updated:

Source:

Editor: HFA, SP

Details of sustainability rating

Database ecoinvent

| Lifecycle | GWP | AP | EP | ODP | POCP | |
|-----------|--------------------------|--------------------------|--------------------------|-------------|---------------|---------|
| (Phases) | [kg CO ₂ -e.] | [kg SO ₂ -e.] | [kg PO ₄ -e.] | [kg R11-e.] | [kg Ethen-e.] | |
| A1 - A3 | | 0.139 | 0.059 | 2,48E-6 | 0.026 | |
| | | | | | | |
| Lifecycle | PERE | PERM | PERT | PENRE | PENRM | PENRT |
| (Phases) | [MJ] | [MJ] | [MJ] | [MJ] | [MJ] | [MJ] |
| A1 - A3 | 130.528 | 783.870 | 914.398 | 478.380 | 28.891 | 507.271 |