

Designation: awroho01a-07 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, SP

# External wall - awroho01a-07


external wall, timber frame construction, not ventilated, without dry lining, with cladding, other surface

#### Performance rating

Fire protection **REI** from inside 30 performance **REI** from outside maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 32,0 kN/m Classified by HFA

| U<br>Diffusion  | 0.23 W/(m <sup>2</sup> K) suitable                                 |
|---|--|
|   |  |
| R <sub>w</sub> (C;C <sub>tr</sub> )<br>L <sub>n,w</sub> (C <sub>l</sub> ) | 50(-2;-7) dB   |
|   |  |
| m   | 70.80 kg/m <sup>2</sup>  |
|   | Diffusion $R_{w}\left(C;C_{tr}\right)$ $L_{n,w}\left(C_{l}\right)$ |

Calculation based on GF



Note: e=625

# Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

|   | Thickness | Building material                 | Thermal performance |             |      | Reaction to fire |    |
|---|-----------|-----------------------------------|---------------------|-------------|------|------------------|----|
|   |           |                                   | λ                   | μ min – max | ρ    | С                | EN |
| Α | 24.0      | larch wood external wall cladding | 0.155               | 150         | 600  | 1.600            | D  |
| В | 24.0      | spruce wood cross battens         | 0.120               | 50          | 450  | 1.600            | D  |
| С | 50.0      | wood wool composite boards        | 0.090               | 2 - 5       | 370  | 2.000            | В  |
| D | 15.0      | fibreboard (MDF)                  | 0.140               | 11          | 600  | 1.700            | D  |
| Е | 160.0     | construction timber (60/; e=*)    | 0.120               | 50          | 450  | 1.600            | D  |
| F | 160.0     | sheep wool [0,041; R=26]          | 0.041               | 1           | 30   | 1.720            | E  |
| G | 15.0      | OSB (sealed with airtight tape)   | 0.130               | 200         | 600  | 1.700            | D  |
| Н | 12.5      | gypsum fibre board or             | 0.320               | 21          | 1000 | 1.100            | A2 |
| Н | 12.5      | gypsum plaster board type DF      | 0.250               | 10          | 800  | 1.050            | A2 |

## Sustainability rating (per m<sup>2</sup>)

Database ecoinvent

OI3<sub>Kon</sub> 20.3

Calculated by HFA



Designation: awroho01a-07 8/2/23 Holzforschung Austria Last updated:

Source:

HFA, SP Editor:

## Details of sustainability rating

#### Database ecoinvent

| Lifecycle | GWP                      | AP                       | EP                       | ODP         | POCP          |       |
|-----------|--------------------------|--------------------------|--------------------------|-------------|---------------|-------|
| (Phases)  | [kg CO <sub>2</sub> -e.] | [kg SO <sub>2</sub> -e.] | [kg PO <sub>4</sub> -e.] | [kg R11-e.] | [kg Ethen-e.] |       |
| A1 - A3   |                          | 0.104                    | 0.043                    | 2,17E-6     | 0.023         |       |
|           |                          |                          |                          |             |               |       |
| Lifecycle | PERE                     | PERM                     | PERT                     | PENRE       | PENRM         | PENRT |
| (Phases)  | [MJ]                     | [MJ]                     | [MJ]                     | [MJ]        | [MJ]          | [MJ]  |
|           |                          |                          |                          |             |               |       |