

Designation: awropi03a-04 8/2/23 Last updated:

Holzforschung Austria Source:

Editor: HFA, SP

## External wall - awropi03a-04

external wall, timber frame construction, not ventilated, with dry lining, with rendering, other surface

#### Performance rating


**REI** from inside 60 Fire protection performance RFI from outside 30 maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 19,2 kN/m Classified by HFA

Thermal performance  Calculated by HFA	U Diffusion	0.13 W/(m <sup>2</sup> K) suitable
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>I</sub> )	48(-3;-6) dB

vertical battens for the dry lining screwed onto the structural timber lead to an Rw(C;Ctr)=45(-1;-5) dB Assessed by MA39

Mass per unit area  $55.80 \text{ kg/m}^2$ 

Calculation based on gypsum plaster board type DF



Note: e=625

## Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
			λ	μ min – max	ρ	С	EN
Α	4.0	plaster	1.000	10 - 35	2000	1.130	A1
В	50.0	Polystyrene EPS-F [0,040]	0.040	20 - 50	17	1.450	E
С	25.0	planking spruce wood	0.120	50	450	1.600	D
D	240.0	construction timber (60/; e=*)	0.120	50	450	1.600	D
E	240.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
F	25.0	planking spruce wood	0.120	50	450	1.600	D
G		vapour barrier sd≥ 16m			1000		
Н	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
I	40.0	mineral wool [040; ≥16; <1000°C] or air layer in type 02	0.040	1	16	1.030	A1
J	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
J	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

# Sustainability rating (per m<sup>2</sup>)

Database ecoinvent OI3<sub>Kon</sub> 28.2 Calculated by HFA



Designation: awropi03a-04 Last updated:

8/2/23 Holzforschung Austria Source:

HFA, SP Editor:

### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.137	0.058	2,41E-6	0.033	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]