dataholz.eu

Designation: Last updated: Source: Editor: awropi04a-10 8/2/23 Holzforschung Austria HFA, SP

External wall - awropi04a-10

external wall, timber frame construction, not ventilated, with dry lining, with rendering, other surface

Performance rating

Fire protection performance	REI from inside REI from outside	60 60		/
maximum ceiling height = Classified by MA39 Classified by HFA	= 3 m; maximum load E _{d,f}	= 32,0 kN/m		
Thermal performance	U Diffusion	0.19 W∕(m ² K) suitable	-	F
Calculated by HFA			P	
Acoustic performance	R _w (C;C _{tr}) L _{n,w} (C _l)	52(-3;-11) dB	-	ŀ
vertical battens for the dr Rw(C;Ctr)=50(-3;-11) dB Assessed by MA39	y lining screwed onto the	structural timber lead to an		C
Mass per unit area	m	56.60 kg∕m ²]

Calculation based on gypsum plaster board type DF

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	rformance			Reaction to fire
			λ	µ min – max	ρ	с	EN
Ą	7.0	plaster	1.000	10 - 35	2000	1.130	A1
В	60.0	wood-fibre insulation board WF-PT [045; 180]	0.045	5 - 7	180	2.100	E
С	160.0	construction timber (60/; e=625)	0.120	50	450	1.600	D
D	160.0	sheep wool [0,041; R=26]	0.041	1	30	1.720	E
E	15.0	OSB (sealed with airtight tape)	0.130	200	600	1.700	D
F	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
G	40.0	sheep wool [0,041; R=26]	0.041	1	30	1.720	E
Н	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
Н	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

Sustainability rating (per m²)

Database ecoinvent

OI3_{Kon}

Calculated by HFA

31.0

dataholz.eu

Designation: Last updated: Source: Editor: awropi04a-10 8/2/23 Holzforschung Austria HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.129	0.057	2,97E-6	0.022	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]

dataholz.eu – Catalogue of timber building materials, components and component connections reviewed to consider thermal, acoustic, fire performance requirements and ecological drivers for timber construction released by accredited testing institutes. These datasheets will generally be accepted as proofs of compliance by building authorities.