dataholz.eu

Designation: Last updated: Source: Editor:

awropi04a-16 8/2/23 Holzforschung Austria HFA, SP

External wall - awropi04a-16

external wall, timber frame construction, not ventilated, with dry lining, with rendering, other surface

Performance rating

Fire protection performance	REI from inside REI from outside	60 60
maximum ceiling height = Classified by HFA Classified by HFA	3 m; maximum load E _{d,f}	_{fi} = 32,0 kN∕m
Germany F60 (from inside/from out		rumont
Load E _{d,fi} according to the Corresponding proof: man		cument
Thermal performance	U Diffusion	0.15 W∕(m ² K) suitable
Calculated by TUM		
Acoustic performance	R _w (C;C _{tr}) L _{n,w} (C _l)	53(-3;-11) dB
Assessed by Müller-BBM		
Mass per unit area	m	65.90 kg∕m ²
Calculation based on gyps	sum plaster board type D	F

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	Reaction to fire			
			λ	µ min – max	ρ	с	EN
١	7.0	plaster	1.000	10 - 35	2000	1.130	A1
3	60.0	wood-fibre insulation board WF-PT [045; 180]	0.045	5 - 7	180	2.100	E
;	200.0	construction timber (60/; e=625)	0.120	50	450	1.600	D
)	200.0	Wood fibre insulation [039; 45]	0.039	1 - 2	45	2.100	E
	15.0	OSB (sealed with airtight tape)	0.130	200	600	1.700	D
	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
5	40.0	Wood fibre insulation [039; 45]	0.039	1 - 2	45	2.100	E
ł	15.0	gypsum plaster board type DF or	0.250	10	800	1.050	A2
ł	15.0	gypsum fibre board	0.320	21	1000	1.100	A2

Sustainability rating (per m²)

Database ecoinvent

Database GaBi (ÖKOBAUDAT) OI3_{Kon} 33.8 Built-in renewable materials 49.370 kg Biogenic carbon in kg CO₂-e. kg CO₂ 72.110 Calculated by HFA Energy use of Primary Energy MJ 1173.740 Share of renewable PE % 37.83 Calculated by TUM

dataholz.eu - Catalogue of timber building materials, components and component connections reviewed to consider thermal, acoustic, fire performance requirements and ecological drivers for timber construction released by accredited testing institutes. These datasheets will generally be accepted as proofs of compliance by building authorities.

dataholz.eu

Designation: Last updated: Source: Editor: awropi04a-16 8/2/23 Holzforschung Austria HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.149	0.066	3,08E-6	0.024	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[LM]	[M]	[M]	[LM]	[MJ]	[MJ]
	116.572	767.654	884.226	563.314	51.328	614.642

Database GaBi (ÖKOBAUDAT)

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.131	0.028	6,48E-7	0.033	
C1 - C4		0.003	0.000	6,31E-8	0.000	
A1 - C4		0.137	0.029	7,21E-7	0.034	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[M]	[LM]	[LM]	[MJ]	[LM]
A1 - A3	441.211	1136.879	1578.588	694.201	59.871	754.160
C1 - C4	2.396	-1131.697	-1129.137	28.863	-58.030	-26.960
A1 - C4	444.085	5.441	450.392	729.657	1.904	737.230