# dataholz.eu


Designation: Last updated: Source: Editor: awropi14a-08 8/2/23 Holzforschung Austria HFA, SP

### External wall - awropi14a-08

external wall, timber frame construction, not ventilated, with dry lining, with rendering, other surface

#### Performance rating

Fire protection performance maximum ceiling height = Classified by HFA	REI from inside REI from outside 3 m; maximum load E <sub>d,fi</sub> = 3	60 90 32,0 kN∕m
Thermal performance	U Diffusion	0.17 W/(m <sup>2</sup> K) suitable
Calculated by HFA		
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>l</sub> )	52(-3;-10) dB
Vertical battens for the dry Rw(C;Ctr)=49(-1;-7) dB Assessed by MA39	lining screwed onto the led	ger beams lead to an
Mass per unit area	m	75.20 kg/m <sup>2</sup>



Calculation based on gypsum plaster board type DF

Note: e=625

### Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	formance			Reaction to fire
			λ	µ min – max	ρ	с	EN
Ą	7.0	plaster	1.000	10 - 35	2000	1.130	A1
В	60.0	wood-fibre insulation board WF-PT [045; 180]	0.045	5 - 7	180	2.100	E
С	10.0	gypsum fibre board	0.320	21	1000	1.100	A2
D	160.0	construction timber (60/; $e=*$ )	0.120	50	450	1.600	D
E	160.0	mineral wool [038; ≥33; ≥1000°C]	0.038	1	33	1.030	A1
F	12.5	gypsum fibre board	0.320	21	1000	1.100	A2
G		vapour barrier sd≥ 3m			1000		
Н	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
	40.0	mineral wool [038; ≥33; ≥1000°C]	0.038	1	33	1.030	A1
	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

### Sustainability rating (per m<sup>2</sup>)

Database ecoinvent

OI3<sub>Kon</sub>

Calculated by HFA

44.6

# dataholz.eu

Designation: Last updated: Source: Editor: awropi14a-08 8/2/23 Holzforschung Austria HFA, SP

#### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.186	0.068	2,97E-6	0.052	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[LM]	[MJ]	[MJ]	[LM]	[M]	[MJ]
	72.335	412.734	485.069	574.092	30.052	604,144

dataholz.eu – Catalogue of timber building materials, components and component connections reviewed to consider thermal, acoustic, fire performance requirements and ecological drivers for timber construction released by accredited testing institutes. These datasheets will generally be accepted as proofs of compliance by building authorities.