# dataholz.eu


Designation: Last updated: Source: Editor: awropi15b-11 8/2/23 Holzforschung Austria HFA, SP

### External wall - awropi15b-11

external wall, timber frame construction, not ventilated, with dry lining, with rendering, other surface

### Performance rating

Fire protection performance	REI from inside REI from outside	60 60
maximum ceiling height = Classified by HFA	- 3 m; maximum ioad E <sub>d,</sub>	fi = 32,0 kN/ m
Thermal performance	U Diffusion	0.18 W∕(m <sup>2</sup> K) suitable
Calculated by HFA		
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>l</sub> )	52(-2;-9) dB
Vertical battens for the dr Rw(C;Ctr)=50(-1;-7) dB Assessed by MA39	y lining screwed onto the	e ledger beams lead to an
Mass per unit area	m	80.30 kg/m <sup>2</sup>



Calculation based on gypsum plaster board type DF

Note: e=400

#### Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	formance			Reaction to fire
			λ	µ min – max	ρ	с	EN
١	7.0	plaster	1.000	10 - 35	2000	1.130	A1
3	60.0	wood-fibre insulation board WF-PT [045; 180]	0.045	5 - 7	180	2.100	E
2	12.0	particleboard P5	0.130	50 - 100	700	1.700	D
)	160.0	construction timber (60/; $e=*$ )	0.120	50	450	1.600	D
	160.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
	16.0	particleboard P4	0.130	50 - 100	700	1.700	D
5		vapour barrier sd≥ 7m			1000		
ł	40.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
	40.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
	15.0	gypsum plaster board type DF or	0.250	10	800	1.050	A2
	15.0	gypsum fibre board	0.320	21	1000	1.100	A2

#### Sustainability rating (per m<sup>2</sup>)

Database ecoinvent

OI3<sub>Kon</sub>

Calculated by HFA

43.3

# dataholz.eu

Designation: Last updated: Source: Editor: awropi15b-11 8/2/23 Holzforschung Austria HFA, SP

#### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.178	0.080	3,37E-6	0.032	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
	[MJ]	[MJ]	[MJ]	[LM]	[MJ]	[MJ]
(Phases)	[]					

dataholz.eu – Catalogue of timber building materials, components and component connections reviewed to consider thermal, acoustic, fire performance requirements and ecological drivers for timber construction released by accredited testing institutes. These datasheets will generally be accepted as proofs of compliance by building authorities.