

Designation: awropi18b-06 8/2/23 Last updated:

Holzforschung Austria Source:

Editor: HFA, SP

# External wall - awropi18b-06

external wall, timber frame construction, not ventilated, with dry lining, with rendering, other surface

### Performance rating


**REI** from inside 60 Fire protection performance RFI from outside 60 maximum ceiling height = 3 m; maximum load  $E_{d,fi}$  = 32,0 kN/m Classified by HFA

Thermal performance  Calculated by HFA	U Diffusion	0.12 W/(m <sup>2</sup> K) suitable
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>l</sub> )	54(-2;-9) dB

Vertical battens for the dry lining screwed onto the ledger beams lead to an Rw(C;Ctr)=51(-1;-7) dB Assessed by MA39

Mass per unit area  $88.60 \text{ kg/m}^2$ 

Calculation based on gypsum plaster board type DF



Note: e=625

## Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness Building material		Thermal performance				Reaction to fire
			λ	μ min – max	ρ	С	EN
Α	7.0	plaster	1.000	10 - 35	2000	1.130	A1
В	60.0	wood-fibre insulation board WF-PT [045; 180]	0.045	5 - 7	180	2.100	E
С	24.0	planking spruce wood	0.120	50	450	1.600	D
D	240.0	construction timber (60/; e=*)	0.120	50	450	1.600	D
E	240.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
F	24.0	planking spruce wood	0.120	50	450	1.600	D
G		vapour barrier sd≥ 7m			1000		
Н	80.0	spruce wood cross battens (a=400) or battens offset)	0.120	50	450	1.600	D
I	80.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
J	15.0	gypsum plaster board type DF or	0.250	10	800	1.050	A2
J	15.0	gypsum fibre board	0.320	21	1000	1.100	A2

## Sustainability rating (per m<sup>2</sup>)

Database ecoinvent OI3<sub>Kon</sub> 41.7 Calculated by HFA



Designation: awropi18b-06 8/2/23 Holzforschung Austria Last updated:

Source:

HFA, SP Editor:

### Details of sustainability rating

### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.197	0.089	3,76E-6	0.035	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]