dataholz.eu

Designation: awropo07a-07
Last updated: 8/2/23
Source: Holzforschung Austria
Editor: HFA, SP

External wall - awropo07a-07

external wall, timber frame construction, not ventilated, without dry lining, with rendering, gypsum plasterboard

Performance rating

Fire protection performance	**REI from inside**	60
	REI from outside	30

maximum ceiling height = 3 m; maximum load $E_{d,fi}$ = 32,0 kN/m
Classified by HFA

Thermal performance	**U**	0.21 W/(m²K)
	Diffusion	suitable

Calculated by HFA

Acoustic performance	**R_w ($C;C_{tr}$)**	44(-2;-6) dB
	$L_{n,w}$ (C_I)	

Assessed by MA39

Mass per unit area	**m**	47.30 kg/m²

Calculation based on gypsum plaster board type DF



Note: e=625

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
			λ	μ min – max	ρ	c	EN
A	4.0	plaster	1.000	10 - 35	2000	1.130	A1
B	50.0	Polystyrene EPS-F [0,040]	0.040	20 - 50	17	1.450	E
C	16.0	particleboard	0.130	50 - 100	700	1.700	D
D	160.0	construction timber (60/..; e=*)	0.120	50	450	1.600	D
E	160.0	sheep wool [0,041; R=26]	0.041	1	30	1.720	E
F	16.0	particleboard	0.130	50 - 100	700	1.700	D
G		vapour barrier sd≥ 17m			1000		
H	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
H	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

Sustainability rating (per m²)

Database ecoinvent

$OI3_{Kon}$	25.5

Calculated by HFA

Details of sustainability rating

Database ecoinvent

Lifecycle (Phases)	GWP [kg CO_2-e.]	AP [kg SO_2-e.]	EP [kg PO_4-e.]	ODP [kg R11-e.]	POCP [kg Ethen-e.]	
A1 - A3		0.090	0.036	1,85E-6	0.026	

Lifecycle (Phases)	PERE [MJ]	PERM [MJ]	PERT [MJ]	PENRE [MJ]	PENRM [MJ]	PENRT [MJ]
A1 - A3	38.473	500.466	538.940	420.138	79.970	500.107