dataholz.eu

Designation: Last updated: Source: Editor:

ddmxxi01a-03 l: 8/2/23 Holzforschung Austria HFA, PLB

Floor towards attic (uninhabitable) - ddmxxi01a-03

floor towards attic (uninhabitable), solid wood construction, not suspended, dry, other surface

Performance rating

| Fire protection performance maximum span = 5 m; ma Classified by HFA | REI aximum load $E_{d,fi}$ = | 30 0,6 kN∕m² | |
|-------------------------------------------------------------------------------|---------------------------------------------------------------------------|---------------------------------------|-----------------------------|
| Germany REI30 Load E _{d,fi} according to the | | on document | |
| Corresponding proof: mar | ufacturer-specific | | |
| Thermal performance | U Diffusion | 0.10 W∕(m ² K) suitable | |
| Calculated by TUM | | | |
| Acoustic performance | R _w (C;C _{tr}) L _{n,w} (C _l) | 44(-2;-7) dB | B |
| Assessed by Müller-BBM | | | |
| Mass per unit area | m | 124.60 kg/m ² | |
| | | | Note: A: pressure-resistant |

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

| | Thickness | Building material | Thermal performance | | | | Reaction to fire |
|---|-----------|---------------------------------------------------------------------------------|---------------------|-------------|-----|-------|------------------|
| | | | λ | µ min – max | ρ | с | EN |
| А | 300.0 | wood-fibre insulation board [0,045; R=160] | 0.045 | 5 - 7 | 160 | 2.100 | E |
| В | | foil (air tight) | | | | | |
| С | 125.0 | cross laminated timber \ge 125mm; 5-ply at least, surface layer at least 27,5 | 0.130 | 50 | 500 | 1.600 | D |
| D | 80.0 | spruce wood battens (50/80; e=400) | 0.120 | 50 | 450 | 1.600 | D |
| Е | 80.0 | Wood fibre insulation [039; 45] | 0.039 | 1 - 2 | 45 | 2.100 | E |
| F | 16.0 | 3-ply solid wood panel | 0.110 | 50 | 400 | 2.500 | D |

Sustainability rating (per m²)

Database ecoinvent

 $\mathsf{OI3}_{\mathsf{Kon}}$ Calculated by HFA

74.0

Database GaBi (ÖKOBAUDAT)

| Built-in renewable materials | kg | 149.620 |
|-------------------------------------------|--------------------|----------|
| Biogenic carbon in kg CO ₂ -e. | kg CO ₂ | 214.770 |
| Energy use of Primary Energy | MJ | 1777.990 |
| Share of renewable PE | % | 41.15 |

Calculated by TUM

dataholz.eu

Designation: Last updated: Source: Editor: ddmxxi01a-03 8/2/23 Holzforschung Austria HFA, PLB

Details of sustainability rating

Database ecoinvent

| Lifecycle | GWP | AP | EP | ODP | POCP | |
|-----------|--------------------------|--------------------------|--------------------------|-------------|---------------|----------|
| (Phases) | [kg CO ₂ -e.] | [kg SO ₂ -e.] | [kg PO ₄ -e.] | [kg R11-e.] | [kg Ethen-e.] | |
| A1 - A3 | | 0.357 | 0.157 | 6,64E-6 | 0.080 | |
| | | | | | | |
| Lifecycle | PERE | PERM | PERT | PENRE | PENRM | PENRT |
| (Phases) | [MJ] | [M] | [LM] | [M] | [M] | [MJ] |
| A1 - A3 | 222.954 | 1991,933 | 2214.887 | 1276,129 | 126.862 | 1402.991 |

Database GaBi (ÖKOBAUDAT)

| Lifecycle | GWP | AP | EP | ODP | POCP | |
|-----------|--------------------------|--------------------------|--------------------------|-------------|---------------|----------|
| (Phases) | [kg CO ₂ -e.] | [kg SO ₂ -e.] | [kg PO ₄ -e.] | [kg R11-e.] | [kg Ethen-e.] | |
| A1 - A3 | | 0.205 | 0.043 | 3,95E-6 | 0.044 | |
| C1 - C4 | | 0.002 | 0.000 | 1,91E-7 | 0.000 | |
| A1 - C4 | | 0.207 | 0.043 | 4,14E-6 | 0.044 | |
| | | | | | | |
| Lifecycle | PERE | PERM | PERT | PENRE | PENRM | PENRT |
| (Phases) | [LM] | [M] | [LM] | [LM] | [MJ] | [M] |
| A1 - A3 | 728.631 | 2225.722 | 2950.572 | 1004.017 | 84.378 | 1087.727 |
| C1 - C4 | 3.040 | -2225.779 | -2222.738 | 42.299 | -67.228 | -24.929 |
| A1 - C4 | 731.671 | -0.058 | 727.833 | 1046.316 | 17.150 | 1062.798 |