

Designation: fdrhbi05a-06 Last updated: 8/2/23

Source: Holzforschung Austria

Editor: HFA, SP

# Flat roof - fdrhbi05a-06

flat roof, timber frame construction, ventilated, with dry lining, not suspended, other surface

## Performance rating

Fire protection

 $\begin{array}{c} \textbf{performance} \\ \textbf{maximum span} = 5 \text{ m; maximum load } E_{d,fi} = 3,66 \text{ kN/m}^2 \\ \textbf{Classified by HFA} \\ \\ \textbf{Thermal performance} \qquad \textbf{U} \\ \textbf{Diffusion} \qquad \textbf{0.22 W/(m}^2 \text{K)} \\ \textbf{Suitable} \\ \\ \textbf{Calculated by HFA} \\ \end{array}$ 


30

Acoustic performance  $R_w$  (C;C<sub>tr</sub>) 48(-4;-9) dB  $L_{n,w}$  (C<sub>1</sub>)

Assessed by  $\mathsf{TGM}$ 

 $\label{eq:mass_per_unit_area} \mbox{Mass per unit area} \qquad \mbox{m} \qquad \qquad 31.90 \mbox{ kg/m}^2$ 

Calculation based on gypsum plaster board type DF



Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

### Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
			λ	μ min – max	ρ	С	EN
Α		trapezoidal sheet metal roofing					A1
В	80.0	spruce wood battens (80/50)	0.120	50	450	1.600	D
С	50.0	spruce wood counter battens (ventilation)	0.120	50	450	1.600	D
D		sarking membrane sd ≤ 0,3 m			1000		E
Ε	22.0	softboard [045; 250] - rigid underlay	0.045	5	250	2.100	E
F	200.0	construction timber (80/; e=800)	0.120	50	450	1.600	D
G	200.0	sheep wool [0,041; R=26]	0.041	1	30	1.720	E
Н		vapour barrier sd≥ 2m			1000		
I	24.0	spruce wood cladding with spacing of cladding boards(24/100); a=400	0.120	50	450	1.600	D
J	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
J	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

#### Sustainability rating (per m<sup>2</sup>)

Database ecoinvent

OI3<sub>Kon</sub> 63.6

Calculated by HFA



Designation: fdrhbi05a-06 Last updated:

8/2/23 Holzforschung Austria Source:

Editor: HFA, SP

### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.248	0.122	3,67E-6	0.046	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	82.577	495.503	578.081	821.006	20,463	841.468