

Designation: fdrhbi06b-04 Last updated: 8/2/23

Source: Holzforschung Austria

Editor: HFA, SP

Flat roof - fdrhbi06b-04

flat roof, timber frame construction, ventilated, with dry lining, not suspended, other surface


Performance rating

Fire protection

60

Assessed by TGM

Calculation based on gypsum plaster board type DF



Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire	
			λ	μ min – max	ρ	С	EN	
Α		Plastic roofing membrane or					E	
Α		sheet metal roofing			7800		A1	
В	24.0	spruce wood closed cladding without spacing of cladding boards	0.120	50	450	1.600	D	
С	80.0	spruce wood counter battens (ventilation)	0.120	50	450	1.600	D	
D		sarking membrane sd ≤ 0,3 m			1000		Е	
Ε	15.0	OSB	0.130	200	600	1.700	D	
F	200.0	construction timber (80/; e=800)	0.120	50	450	1.600	D	
G	200.0	mineral wool [035; 50; <1000°C]	0.035	1	50	1.030	A1	
Н		vapour barrier sd≥ 8m			1000			
I	15.0	OSB	0.130	200	600	1.700	D	
J	50.0	spruce wood cross battens (50/80;a=400)	0.120	50	450	1.600	D	
K	50.0	mineral wool [035; 50; <1000°C]	0.035	1	50	1.030	A1	
L	25.0	gypsum plaster board type DF (2x12,5 mm) or	0.250	10	800	1.050	A2	
L	25.0	gypsum fibre board (2x12,5 mm)	0.320	21	1000	1.100	A2	

Sustainability rating (per m²)

Database ecoinvent

OI3_{Kon} 68.6

Calculated by HFA



Designation: fdrhbi06b-04 Last updated:

8/2/23 Holzforschung Austria Source:

HFA, SP Editor:

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.293	0.134	5,04E-6	0.048	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	160.135	755.065	915.200	944.923	31.226	976.149