

Designation: iwrxx003b-01 Last updated: 8/2/23

Source: Holzforschung Austria

Editor: HFA, SP

Internal wall - iwrxxo03b-01

internal wall, timber frame construction, without dry lining, other surface


Performance rating

Fire protection REI 90 performance maximum ceiling height = 3 m; maximum load $E_{d,fi}$ = 19,0 kN/m Classified by HFA

Acoustic performance R_{w} (C;Ctr) $L_{n,w}$ (C₁)

Mass per unit area m 69.20 kg/m²

Calculation based on GF



Note: The fire resistance is only valid when wall is used as partition with only one side exposed to fire. (B=60/160); e=625

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
			λ	μ min – max	ρ	С	EN
Α	30.0	gypsum plaster boards type DF (2x15 mm) or	0.250	10	800	1.050	A2
Α	30.0	gypsum fibre board (2x15 mm)	0.320	21	1000	1.100	A2
В	160.0	construction timber (60/100 or 60/160; e=*)	0.120	50	450	1.600	D
С	100.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
D	30.0	gypsum plaster boards type DF (2x15 mm) or	0.250	10	800	1.050	A2
D	30.0	gypsum fibre board (2x15 mm)	0.320	21	1000	1.100	A2

Sustainability rating (per m²)

Database ecoinvent

OI3_{Kon} 17.9

Calculated by HFA



Designation: iwrxxo03b-01 Last updated:

8/2/23 Holzforschung Austria Source:

Editor: HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.059	0.028	1,87E-6	0.009	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	35.670	125.783	161.453	284.532	0.000	284.532