

Designation: sdrhbi02a-04 Last updated: 8/2/23

Source: Holzforschung Austria

Editor: HFA, SP

Pitched roof - sdrhbi02a-04

pitched roof, timber frame construction, ventilated, with dry lining, not suspended, other surface

Performance rating

Fire protection REI 30 performance

maximum span = 5 m; maximum load $E_{\rm d,fi}$ = 3,66 kN/m² (rafter 80/200 without roofing, full formwork, counter battens and OSB)

Classified by HFA


Germany


F30

Load E_{d,fi} according to the German certification document

Corresponding proof: DIN 4102-4:2016-05, Tabelle 10.19, Zeile 1

Thermal performance	U Diffusion	0.17 W/(m ² K) suitable
Calculated by TUM		
Acoustic performance	R _w (C;C _{tr}) L _{n,w} (C _l)	48(-1;-7) dB
Assessed by Müller-BBM		
Mass per unit area	m	72.40 kg/m ²





Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				
			λ	μ min – max	ρ	С	EN
Α		sheet metal roofing on structured separation layer			7800		A1
В	24.0	spruce wood full formwork	0.120	50	450	1.600	D
С	80.0	spruce wood counter battens (40/80)	0.120	50	450	1.600	D
D		sarking membrane sd ≤ 0,3m			1000		Е
Е	24.0	planking spruce wood full formwork	0.120	50	450	1.600	D
F	240.0	construction timber (80/*; e=625)	0.120	50	450	1.600	D
G	240.0	Cellulose fibre [040; 50]	0.040	1	50	2.000	E
Н	15.0	OSB airtight	0.130	200	600	1.700	D
I	24.0	spruce wood cladding with spacing of cladding boards(24/100); a=400	0.120	50	450	1.600	D
J	12.5	gypsum plaster board type DF	0.250	10	800	1.050	A2

Sustainability rating (per m²)

Database ecoinvent		Database GaBi (ÖKOBAUDAT)			
OI3 _{Kon}	26.4	Built-in renewable materials	kg	67.670	
Calculated by HFA		Biogenic carbon in kg CO ₂ -e.	kg CO ₂	96.860	
Carcalated by THT		Energy use of Primary Energy	MJ	795.190	
		Share of renewable PE	%	33.49	
		Calculated by TUM			



Designation: sdrhbi02a-04 8/2/23 Holzforschung Austria Last updated:

Source:

Editor: HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.157	0.071	2,29E-6	0.034	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	152.910	948.291	1101.200	452.990	17.244	470.234

Database GaBi (ÖKOBAUDAT)

Lifecycle	GWP	AP	EP	ODP	POCP
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]
A1 - A3		0.124	0.019	1,19E-6	0.027
C1 - C4		0.006	0.008	1,56E-7	0.001
A1 - C4		0.131	0.027	1,35E-6	0.028

Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	265.026	1113.998	1382.768	506.213	79.122	585.484
C1 - C4	0.936	-936.170	-935.235	17.405	-6.480	10.926
A1 - C4	266.341	178.087	448.172	528.848	72.694	601.690