

Designation: sdrhzi04a-07 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, SP

### Pitched roof - sdrhzi04a-07

pitched roof, timber frame construction, ventilated, with dry lining, not suspended, other surface

### Performance rating

Fire protection performance

maximum span = 5 m; maximum load  $E_{d,fi}$  = 2,62 kN/m² (rafter 60/200 without roofing, counter battens and battens)

Classified by HFA

Classified by HFA

#### Germany


F30


Load  $E_{d,fi}$  according to the German certification document

Corresponding proof: DIN 4102-4:2016-05, Tabelle 10.19, Zeile 1

Thermal performance	U Diffusion	0.19 W/(m <sup>2</sup> K) suitable
Calculated by TUM		
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>l</sub> )	53(-2;-8) dB
Assessed by Müller-BBM		
Mass per unit area	m	102.10 kg/m <sup>2</sup>

Calculation based on gypsum plaster board type DF





Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

# Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal performance				Reaction to fire
			λ	μ min – max	ρ	С	EN
Α		concrete roof tile or tiled roof			2100		A1
В	30.0	spruce wood battens (30/50)	0.120	50	450	1.600	D
С	50.0	spruce wood counter battens (Austria: minimum height 50 mm), Germany 30 mm	0.120	50	450	1.600	D
D	22.0	softboard [045; 250] - rigid underlay	0.045	5	250	2.100	E
Е	200.0	construction timber (80/; e=625)	0.120	50	450	1.600	D
F	200.0	Wood fibre insulation [039; 45]	0.039	1 - 2	45	2.100	E
G	15.0	OSB (sealed with airtight tape)	0.130	200	600	1.700	D
Н	24.0	spruce wood cladding with spacing of cladding boards(24/100); a=400	0.120	50	450	1.600	D
I	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
I	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

# Sustainability rating (per m<sup>2</sup>)

Database ecoinvent		Database GaBi (ÖKOBAUDAT)				
OI3 <sub>Kon</sub>	23.7	Built-in renewable materials	kg	43.250		
Calculated by HFA		Biogenic carbon in kg CO <sub>2</sub> -e. Energy use of Primary Energy	kg CO₂ MJ	63.520 1192.800		
		Share of renewable PE	%	30.90		

Calculated by TUM



Designation: sdrhzi04a-07 8/2/23 Holzforschung Austria Last updated:

Source:

Editor: HFA, SP

### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.106	0.048	2,65E-6	0.022	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	106.167	670.525	776.692	429.361	33.304	462.666

#### Database GaBi (ÖKOBAUDAT)

Lifecycle	GWP	AP	EP	ODP	POCP
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]
A1 - A3		0.118	0.024	7,18E-7	0.030
C1 - C4		0.007	0.001	7,05E-8	0.001
A1 - C4		0.128	0.025	7,96E-7	0.030

Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	364.347	995.754	1361.173	775.644	42.132	817.900
C1 - C4	3.174	-990.584	-987.410	34.194	-41.190	-6.996
A1 - C4	368.598	5.429	375.099	824.202	0.994	825.319