

Designation: sdrhzi06a-04 Last updated: 8/2/23

Source: Holzforschung Austria

Editor: HFA, SP

Pitched roof - sdrhzi06a-04

pitched roof, timber frame construction, ventilated, with dry lining, not suspended, other surface

Performance rating

Classified by HFA


 $\begin{tabular}{lll} Fire protection & REI & 30 \\ performance & & & \\ maximum span = 5 m; maximum load $E_{d,fi} = 2,62 kN/m^2$ \\ \end{tabular}$


Thermal performance Calculated by HFA	U Diffusion	0.16 W/(m ² K) suitable
Acoustic performance	R _w (C;C _{tr}) L _{n,w} (C _l)	53(-3;-9) dB

with a tiled roof Rw = 52 dB Assessed by TGM

 $\label{eq:mass_per_unit_area} \mbox{Mass per unit area} \qquad \mbox{m} \qquad \qquad 58.00 \mbox{ kg/m}^2$

Calculation based on gypsum plaster board type DF





Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	rformance			Reaction to fire
			λ	μ min – max	ρ	С	EN
Α		concrete roof tile or tiled roof			2100		A1
В	30.0	spruce wood battens (30/50)	0.120	50	450	1.600	D
С	50.0	spruce wood counter battens (minimum height 50 mm)	0.120	50	450	1.600	D
D		sarking membrane sd ≤ 0,3 m			1000		Е
E	24.0	planking spruce wood closed cladding without spacing of cladding boards	0.120	50	450	1.600	D
F	200.0	construction timber (80/; e=800)	0.120	50	450	1.600	D
G	200.0	mineral wool [035; 50; <1000°C]	0.035	1	50	1.030	A1
Н	15.0	OSB (sealed with airtight tape)	0.130	200	600	1.700	D
1	50.0	spruce wood cross battens (50/80;a=400)	0.120	50	450	1.600	D
J	50.0	mineral wool [035; 50; <1000°C]	0.035	1	50	1.030	A1
K	12.5	gypsum plaster board type DF or	0.250	10	800	1.050	A2
K	12.5	gypsum fibre board	0.320	21	1000	1.100	A2

Sustainability rating (per m²)

Database ecoinvent
Ol3_{Kon} 56.5

Calculated by HFA



Designation: sdrhzi06a-04 Last updated:

8/2/23 Holzforschung Austria Source:

Editor: HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.241	0.110	4,84E-6	0.040	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Dlanes)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
(Phases)	[LAI]	[ivio]	[ivis]	F	f	[]