

Designation: sdrhzi07b-01 Last updated: 8/2/23

Source: Holzforschung Austria

Editor: HFA, SP

# Pitched roof - sdrhzi07b-01

pitched roof, timber frame construction, ventilated, with dry lining, not suspended, other surface

## Performance rating

Fire protection


 $\begin{array}{c} \textbf{performance} \\ \textbf{maximum span} = 5 \text{ m; maximum load } E_{d,fi} = 3,66 \text{ kN/m}^2 \\ \textbf{Classified by HFA} \\ \hline \\ \textbf{Thermal performance} & \textbf{U} & 0.19 \text{ W/(m}^2 \text{K)} \\ \textbf{Diffusion} & \text{suitable} \\ \hline \\ \textbf{Calculated by HFA} \\ \hline \\ \textbf{Acoustic performance} & \textbf{R}_{\textbf{w}} \textbf{(C;C}_{\textbf{t}}\textbf{)} & 53(-1;-7) \text{ dB} \\ \textbf{L}_{\textbf{n,w}} \textbf{(Cj)} \\ \hline \end{array}$ 


60

with a tiled roof Rw = 51 (-1; -7) dBAssessed by TGM

 $\begin{tabular}{lll} \begin{tabular}{lll} \begin{$ 

Calculation based on gypsum plaster board type DF





Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

#### Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

|   | Thickness | Building material   | Thermal performance |             |      |       | Reaction to fire |
|---|-----------|---|---------------------|-------------|------|-------|------------------|
|   |           |   | λ                   | μ min – max | ρ    | С     | EN               |
| Α |           | concrete roof tile or tiled roof                                    |                     |             | 2100 |       | A1               |
| В | 30.0      | spruce wood battens (30/50)   | 0.120               | 50          | 450  | 1.600 | D                |
| С | 50.0      | spruce wood counter battens (minimum height 50 mm)                  | 0.120               | 50          | 450  | 1.600 | D                |
| D |           | sarking membrane sd ≤ 0,3 m   |                     |             | 1000 |       | Е                |
| E | 12.0      | OSB   | 0.130               | 200         | 600  | 1.700 | D                |
| F | 220.0     | construction timber (80/; e=800)                                    | 0.120               | 50          | 450  | 1.600 | D                |
| G | 220.0     | mineral wool [040; ≥16; <1000°C]                                    | 0.040               | 1           | 16   | 1.030 | A1               |
| Н | 15.0      | OSB   | 0.130               | 200         | 600  | 1.700 | D                |
| I |           | vapour barrier sd≥ 11m  |                     |             | 1000 |       |                  |
| J | 24.0      | spruce wood cladding with spacing of cladding boards(24/100); a=400 | 0.120               | 50          | 450  | 1.600 | D                |
| K | 25.0      | gypsum plaster board type DF (2x12,5 mm) or                         | 0.250               | 10          | 800  | 1.050 | A2               |
| K | 25.0      | gypsum fibre board (2x12,5 mm)                                      | 0.320               | 21          | 1000 | 1.100 | A2               |

#### Sustainability rating (per m<sup>2</sup>)

| Database ecoinvent |      |  |  |  |  |  |
|--------------------|------|--|--|--|--|--|
| OI3 <sub>Kon</sub> | 33.3 |  |  |  |  |  |
| Calculated by HFA  |      |  |  |  |  |  |



Designation: sdrhzi07b-01 Last updated:

8/2/23 Holzforschung Austria Source:

Editor: HFA, SP

### Details of sustainability rating

#### Database ecoinvent

| Lifecycle | GWP                      | AP                       | EP                       | ODP         | POCP          |         |
|-----------|--------------------------|--------------------------|--------------------------|-------------|---------------|---------|
| (Phases)  | [kg CO <sub>2</sub> -e.] | [kg SO <sub>2</sub> -e.] | [kg PO <sub>4</sub> -e.] | [kg R11-e.] | [kg Ethen-e.] |         |
| A1 - A3   |                          | 0.139                    | 0.063                    | 3.25E-6     | 0.026         |         |
|           |                          |                          |                          |             |               |         |
| Lifecycle | PERE                     | PERM                     | PERT                     | PENRE       | PENRM         | PENRT   |
| (Phases)  | [MJ]                     | [MJ]                     | [MJ]                     | [MJ]        | [MJ]          | [MJ]    |
| A1 - A3   | 115.924                  | 566.308                  | 682.233                  | 519.884     | 30.376        | 550.260 |