

Designation: sdrhzi08b-02 8/2/23 Last updated:

Holzforschung Austria Source:

Editor: HFA, SP

# Pitched roof - sdrhzi08b-02

pitched roof, timber frame construction, ventilated, with dry lining, not suspended, other surface

# Performance rating


Fire protection performance maximum span = 5 m; maximum load  $E_{d,fi}$  = 3,66 kN/m<sup>2</sup> Classified by HFA


Thermal performance	U Diffusion	0.17 W/(m <sup>2</sup> K) suitable
Calculated by HFA		
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>I</sub> )	53(-2;-8) dB
with a tiled roof Rw = 51	(-2; -8) dB	

Assessed by TGM

Mass per unit area  $48.90 \text{ kg/m}^2$ 

Calculation based on gypsum plaster board type DF





Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

# Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	rformance			Reaction to fire
			λ	μ min – max	ρ	С	EN
Α		concrete roof tile or tiled roof			2100		A1
В	30.0	spruce wood battens (30/50)	0.120	50	450	1.600	D
С	50.0	spruce wood counter battens (minimum height 50 mm)	0.120	50	450	1.600	D
D	15.0	fibreboard (MDF)	0.140	11	600	1.700	D
Е	220.0	construction timber (80/; e=800)	0.120	50	450	1.600	D
F	220.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
G		vapour barrier sd≥ 1 m			1000		
Н	50.0	spruce wood cross battens (50/80;a=400)	0.120	50	450	1.600	D
I	50.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
J	25.0	gypsum plaster board type DF (2x12,5 mm) or	0.250	10	800	1.050	A2
J	25.0	gypsum fibre board (2x12,5 mm)	0.320	21	1000	1.100	A2

### Sustainability rating (per m<sup>2</sup>)

Database ecoinvent

OI3<sub>Kon</sub> 34.3

Calculated by HFA



Designation: sdrhzi08b-02 Last updated:

8/2/23 Holzforschung Austria Source:

HFA, SP Editor:

#### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.136	0.061	3,00E-6	0.024	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MI]	[MJ]	[MJ]	[MJ]	[MJ]
			i		46.624	