

Designation: sdrhzi08b-03 Last updated: 8/2/23

Holzforschung Austria Source:

Editor: HFA, SP

Pitched roof - sdrhzi08b-03

pitched roof, timber frame construction, ventilated, with dry lining, not suspended, other surface

Performance rating

Fire protection


performance maximum span = 5 m; maximum load $E_{d,fi}$ = 3,66 kN/m² Classified by HFA Thermal performance U $0.16 \text{ W/(m}^2\text{K)}$ Diffusion suitable Calculated by HFA Acoustic performance R_w (C;C_{tr}) 54(-2;-9) dB $L_{n,w}$ (C_I)


60

with a tiled roof Rw = 52 (-2; -9) dBAssessed by TGM

Mass per unit area 50.20 kg/m^2

Calculation based on gypsum plaster board type DF





Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

| | Thickness | Building material | Thermal pe | Thermal performance | | | |
|---|-----------|--|------------|---------------------|------|-------|----|
| | | | λ | μ min – max | ρ | С | EN |
| Α | | concrete roof tile or tiled roof | | | 2100 | | A1 |
| В | 30.0 | spruce wood battens (30/50) | 0.120 | 50 | 450 | 1.600 | D |
| С | 50.0 | spruce wood counter battens (minimum height 50 mm) | 0.120 | 50 | 450 | 1.600 | D |
| D | 15.0 | fibreboard (MDF) | 0.140 | 11 | 600 | 1.700 | D |
| E | 240.0 | construction timber (80/; e=800) | 0.120 | 50 | 450 | 1.600 | D |
| F | 240.0 | mineral wool [040; ≥16; <1000°C] | 0.040 | 1 | 16 | 1.030 | A1 |
| G | | vapour barrier sd≥ 1 m | | | 1000 | | |
| Н | 50.0 | spruce wood cross battens (50/80;a=400) | 0.120 | 50 | 450 | 1.600 | D |
| I | 50.0 | mineral wool [040; ≥16; <1000°C] | 0.040 | 1 | 16 | 1.030 | A1 |
| J | 25.0 | gypsum plaster board type DF (2x12,5 mm) or | 0.250 | 10 | 800 | 1.050 | A2 |
| J | 25.0 | gypsum fibre board (2x12,5 mm) | 0.320 | 21 | 1000 | 1.100 | A2 |

Sustainability rating (per m²)

| Database ecoinvent | | | | | | |
|--------------------|------|--|--|--|--|--|
| OI3 _{Kon} | 35.6 | | | | | |
| Calculated by HFA | | | | | | |



Designation: sdrhzi08b-03 Last updated:

8/2/23 Holzforschung Austria Source:

HFA, SP Editor:

Details of sustainability rating

Database ecoinvent

| | i . | 1 | | | | |
|-----------|--------------------------|--------------------------|--------------------------|-------------|---------------|---------|
| Lifecycle | GWP | AP | EP | ODP | POCP | |
| (Phases) | [kg CO ₂ -e.] | [kg SO ₂ -e.] | [kg PO ₄ -e.] | [kg R11-e.] | [kg Ethen-e.] | |
| A1 - A3 | | 0.142 | 0.063 | 3,09E-6 | 0.025 | |
| | | | | | | |
| Lifecycle | PERE | PERM | PERT | PENRE | PENRM | PENRT |
| (Phases) | [MJ] | [MI] | [MJ] | [MJ] | [MJ] | [MJ] |
| A1 - A3 | 88.015 | 508.681 | 596.696 | 528.318 | 46.624 | 574.943 |