

Designation: sdrhzi08b-07 8/2/23 Last updated:

Holzforschung Austria Source:

Editor: HFA, SP

Pitched roof - sdrhzi08b-07

pitched roof, timber frame construction, ventilated, with dry lining, not suspended, other surface

Performance rating


60 Fire protection performance maximum span = 5 m; maximum load $E_{d,fi}$ = 3,66 kN/m² Classified by HFA


Thermal performance	U Diffusion	$0.20 \text{ W/(m}^2\text{K)}$ suitable
Calculated by HFA		
Acoustic performance	R_w (C;C _{tr}) $L_{n,w}$ (C _l)	53(-4;-10) dB
50 - 51 - 5 B - 51	(4 10) ID	

with a tiled roof Rw = 51 (-4; -10) dBAssessed by TGM

Mass per unit area 47.60 kg/m^2

Calculation based on gypsum plaster board type DF





Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	ness Building material Thermal performance					Reaction to fire	
			λ	μ min – max	ρ	С	EN	
Α		concrete roof tile or tiled roof			2100		A1	
В	30.0	spruce wood battens (30/50)	0.120	50	450	1.600	D	
С	50.0	spruce wood counter battens (minimum height 50 mm)	0.120	50	450	1.600	D	
D	15.0	fibreboard (MDF)	0.140	11	600	1.700	D	
E	200.0	construction timber (80/; e=800)	0.120	50	450	1.600	D	
F	200.0	sheep wool [0,041; R=26]	0.041	1	30	1.720	E	
G		vapour barrier sd≥ 1 m			1000			
Н	50.0	spruce wood cross battens (50/80;a=400)	0.120	50	450	1.600	D	
I	50.0	sheep wool [0,041; R=26]	0.041	1	30	1.720	E	
J	25.0	gypsum plaster board type DF (2x12,5 mm) or	0.250	10	800	1.050	A2	
J	25.0	gypsum fibre board (2x12,5 mm)	0.320	21	1000	1.100	A2	

Sustainability rating (per m²)

Database ecoinvent

OI3_{Kon} 25.7

Calculated by HFA



Designation: sdrhzi08b-07 8/2/23 Holzforschung Austria Last updated:

Source:

Editor: HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.095	0.042	2,73E-6	0.021	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
(Phases)	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]	[MJ]
A1 - A3	77.284	610.977	688.260	439.048	47.944	486.992