

Designation: sdrhzi09b-00 8/2/23 Last updated:

Holzforschung Austria Source:

Editor: HFA, SP

# Pitched roof - sdrhzi09b-00

pitched roof, timber frame construction, ventilated, with dry lining, not suspended, other surface

## Performance rating


Fire protection performance maximum span = 5 m; maximum load  $E_{d,fi}$  = 3,66 kN/m<sup>2</sup> Classified by HFA


Thermal performance	U Diffusion	0.21 W/(m <sup>2</sup> K) suitable
Calculated by HFA		
Acoustic performance	R <sub>w</sub> (C;C <sub>tr</sub> ) L <sub>n,w</sub> (C <sub>l</sub> )	53(-2;-8) dB
with a tiled roof Rw = 51	(-2; -8) dB	

Assessed by TGM

Mass per unit area  $54.60 \text{ kg/m}^2$ 

Calculation based on gypsum plaster board type DF





Note: The design of the under-roof construction and of the counterbattens have to be specified according to the roof pitch and the national requirements.

#### Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	rformance			Reaction to fire
			λ	μ min – max	ρ	С	EN
Α		concrete roof tile or tiled roof			2100		A1
В	30.0	spruce wood battens (30/50)	0.120	50	450	1.600	D
С	50.0	spruce wood counter battens (minimum height 50 mm)	0.120	50	450	1.600	D
D	15.0	fibreboard (MDF)	0.140	11	600	1.700	D
Ε	200.0	construction timber (80/; e=800)	0.120	50	450	1.600	D
F	200.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
G	15.0	OSB (sealed with airtight tape)	0.130	200	600	1.700	D
Н	24.0	spruce wood cladding with spacing of cladding boards(24/100); a=400	0.120	50	450	1.600	D
1	25.0	gypsum plaster board type DF (2x12,5 mm) or	0.250	10	800	1.050	A2
1	25.0	gypsum fibre board (2x12,5 mm)	0.320	21	1000	1.100	A2

## Sustainability rating (per m<sup>2</sup>)

Database ecoinvent	
OI3 <sub>Kon</sub>	30.7

Calculated by HFA



Designation: sdrhzi09b-00 8/2/23 Holzforschung Austria Last updated:

Source:

HFA, SP Editor:

### Details of sustainability rating

#### Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO <sub>2</sub> -e.]	[kg SO <sub>2</sub> -e.]	[kg PO <sub>4</sub> -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.131	0.059	2,98E-6	0.023	
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
Lifecycle (Phases)	PERE [MJ]	PERM [MJ]	PERT [MJ]	PENRE [MJ]	PENRM [MJ]	PENRT [MJ]