dataholz.eu


twrxxo03b-03 8/2/23 Holzforschung Austria HFA, SP

Compartment wall - twrxxo03b-03

compartment wall, timber frame construction, without dry lining, double-layer, other surface

Performance rating

Fire protection performance	REI	60
apply to each individual lu height = 3 m; maximum lu Classified by MA39 Classified by HFA	5	wall: EI90; maximum ceiling
Thermal performance	U Diffusion	0.19 W∕(m ² K) suitable
Calculated by HFA		
Acoustic performance	R _w (C;C _{tr}) L _{n,w} (C _l)	59(-2;-10) dB
Assessed by MA39		
Mass per unit area	m	103.50 kg/m ²
Calculation based on gyp	sum plaster board type DF	



lation based on gypsum plaster board type Df

Note: layer A, D, F, I: planking 2x12,5mm; e=625

Register of building materials used for this application, cross-section (from outside to inside, dimensions in mm)

	Thickness	Building material	Thermal per	formance			Reaction to fire
			λ	µ min – max	ρ	с	EN
١	25.0	gypsum plaster board type DF or	0.250	10	800	1.050	A2
١	25.0	gypsum fibre board	0.320	21	1000	1.100	A2
3	100.0	construction timber (60/100; $e=*$)	0.120	50	450	1.600	D
;	100.0	cellulose fibre [0,040; R=55]	0.040	1 - 2	55	2.000	В
)	25.0	gypsum plaster board type DF or	0.250	10	800	1.050	A2
)	25.0	gypsum fibre board	0.320	21	1000	1.100	A2
	20.0	mineral wool [040; ≥16; <1000°C]	0.040	1	16	1.030	A1
	25.0	gypsum plaster board type DF or	0.250	10	800	1.050	A2
	25.0	gypsum fibre board	0.320	21	1000	1.100	A2
5	100.0	construction timber (60/100; e=*)	0.120	50	450	1.600	D
ł	100.0	cellulose fibre [0,040; R=55]	0.040	1 - 2	55	2.000	В
	25.0	gypsum plaster board type DF or	0.250	10	800	1.050	A2
	25.0	gypsum fibre board	0.320	21	1000	1.100	A2

Sustainability rating (per m²)

Database ecoinvent

OI3_{Kon}

Calculated by HFA

26.3

dataholz.eu

Designation: Last updated: Source: Editor: twrxxo03b-03 8/2/23 Holzforschung Austria HFA, SP

Details of sustainability rating

Database ecoinvent

Lifecycle	GWP	AP	EP	ODP	POCP	
(Phases)	[kg CO ₂ -e.]	[kg SO ₂ -e.]	[kg PO ₄ -e.]	[kg R11-e.]	[kg Ethen-e.]	
A1 - A3		0.092	0.042	2,87E-6	0.013	
						1
Lifecycle	PERE	PERM	PERT	PENRE	PENRM	PENRT
Lifecycle (Phases)	PERE [MJ]	PERM [MJ]	[MJ]	PENRE [MJ]	[MJ]	PENRT [MJ]

dataholz.eu – Catalogue of timber building materials, components and component connections reviewed to consider thermal, acoustic, fire performance requirements and ecological drivers for timber construction released by accredited testing institutes. These datasheets will generally be accepted as proofs of compliance by building authorities.